

**BULK FILL MADE EASY.  
PACKABLE OR FLOWABLE  
IT'S YOUR CHOICE!**



x-tra fil/x-tra base®

## **x-tra fil**

**PACKABLE POSTERIOR  
BULK FILL COMPOSITE  
CURE 4MM IN 10 SEC**

## **x-tra base**

**FLOWABLE POSTERIOR  
BULK BASE COMPOSITE  
CURE 4MM IN 10 SEC**

## x-tra base®

### FLOWABLE BULK FILL BASE COMPOSITE

x-tra base is a flowable, self-leveling base liner composite which allows increments of up to 4mm to be placed in a single step and light cured in only 10 seconds when using the Universal shade.

#### Indications

- Lining (restoration base) for class I and II cavities
- Cavity lining (base layer) for class I and II cavities.

#### Low shrinkage stress and outstanding physical properties

##### for long lasting posterior restorations

VOCO's advanced polymer technology gives x-tra base up to 60% lower shrinkage stress than conventional flowable composites.

##### Suitable for facial walls

A lower water absorption and solubility based on a higher filler content leads to increased hardness. This allows x-tra base to

#### Outstanding quality – scientifically proven

	x-tra base® Universal shade (VOCO)	SDR™ Universal shade (Dentsply)	Venus® Bulk Fill Universal shade (Heraeus Kulzer)
Curing time [s] with 4-mm increment thickness (as per instructions for use)	10	20	20
Radiopacity [% AI] (as per ISO 4049)	350	306	247
Shrinkage stress [MPa] (Bioman method)	5.93	6.54	6.79
Shrinkage [% v/v] (bonded disc)	2.54	2.57	3.25
Filler content [%] (as per instructions for use)	75	approx. 68	65
Flexural strength after thermocycling, 3000 cycles [MPa] (as per ISO 4049)	141	126	94
Compressive strength [MPa] (as per ISO 9917)	357	220	328
Micro Vickers Hardness [MHV] <sup>1</sup>	100	61	52
Toothbrush abrasion [µm] (abrasion as per ISO 11609, measurement by means of laser profilometry)	16	19	29
Water absorption / solubility [µg/mm³] (as per ISO 4049)	7.73 / < 0.1	20.18 / 2.89	24.90 / 0.41

Source: VOCO GmbH internal measurements 2011,  
SDR and Venus Bulk Fill are not registered trademarks of VOCO GmbH.

<sup>1</sup> Source: Prof. Dr. D. Behrend, University of Rostock, 2011



### Save up to 50% on procedure time

x-tra base not only makes placement easier, it can also cut your procedure time in half. It saves you two increment layers. The x-tra base universal shade cures in only 10 seconds, which is half the setting time of other bulk fill flowable composites.

Procedures	x-tra base®		Conventional Procedure	
	Application Time	Curing Time	Application Time	Curing Time
Flowable Liner	30s	10s	20s	40s
Universal Composite 1. layer			30s	20s
Universal Composite 2. layer			30s	20s
Occlusal Layer	60s	20s	60s	20s
<b>Total Time</b>	<b>2min</b>		<b>4min</b>	

### Two delivery systems

Choose between hygienic unit dose or economical syringe delivery systems.

The x-tra base unit dose caps come with an extra long bendable needle tip. Bend them the way you need for your procedure.

The x-tra base tip is 60% longer than the leading bulk fill flowable material, giving you easier access in hard to reach areas.

### Two shades

x-tra base is available in Universal and A2 shades. In most cases, the extremely quick to cure Universal shade is the first

Universal



A2



### Excellent handling with smart self-leveling effect

The flowable consistency makes it easy for the material to flow into the smallest undercuts. The smart self-leveling effect saves time. x-tra base will level by itself without slumping out



1 A fully prepared cavity



2 Coating of the cavity walls with Futurabond DC



3 Start at the deepest point in the cavity...



4 ... and fill up to 4mm with x-tra base



5 Apply a 2-mm occlusal layer of GrandioSO



6 Finished restoration

## x-tra fil

### PACKABLE BULK FILL POSTERIOR COMPOSITE


x-tra fil is a posterior, universal shade composite, that allows the clinician to cure 4mm layers in 10 seconds. It is the perfect match for patients with a limited budget where esthetics are secondary and your office time counts. Use with Futurabond DC and you can complete a 4mm posterior restoration in less than 2 minutes. x-tra fil has a smooth and non-sticky consistency that does not slump. A high radiopacity of 330% AI makes x-ray identification easy.

**Bond, fill, sculpt and cure a 4mm restoration in less than 2 min**

When speed is the primary objective, x-tra fil and Futurabond DC

#### Indications

- Restorations class I and II in bulk-filling technique
- Core build-up



#### Multihybrid technology for uncompromising results

x-tra fil's speed does not compromise the quality of the restoration. The modern composite is based on state of the art multihybrid technology. By optimizing the filler sizes, the material

Technical Data			
Filler Content	86% by weight	Wear (ACTA)	43µm
Shrinkage Stress	3.5 MPa	Radiopacity	330% AI
Volumetric Shrinkage	1.7%	Flexural Strength after TC	145MPa
Surface Hardness	142MHV		



1 An amalgam restoration in need of replacement



2 The glistening surface indicates excellent wetting with the bond before polymerization



3 Start at the deepest point in the cavity ...



4 Filling the cavity in 4mm increments



5 Filling the palatal cavity



6 Finished restoration after occlusal verification





## Futurabond DC + + + + +

VOCO America, Inc.  
888.658.2584  
www.vocoamerica.com

### Description

**Futurabond DC** is a dual-cured, self-etching bonding agent (7<sup>th</sup>-generation) that is reinforced with nanoparticles. It is indicated for use with direct light-, dual- or self-cured composite restorations and core build-ups plus cementation of posts and indirect restorations (inlays, crowns and bridges) with light-, dual-, or self-cured resin composite cements. The system includes two liquids - the self-etching bonding agent and the dual-cured activator.

**Futurabond DC** is available in *SingleDose* blister packs or in 4-ml bottles. To use the blister pack, press the blister to allow mixing of the two liquids. Puncture the foil with the applicator brush and stir. Apply to the tooth for 20 seconds, air dry and light cure for 10 seconds. **Futurabond DC SingleDose** was evaluated by 18 Editors in over 370 cases. This product received a 96% clinical rating.

### Suggested Retail Cost

- \$112.95/ kit of 50 *SingleDose*
- \$339.95/ kit of 200 *SingleDose*

### Evaluation Protocol

- **Futurabond DC SingleDose** was evaluated by 18 Editors in over 370 cases.

### Editors' Observations

#### Manufacturer Instructions and Packaging

The *SingleDose* packets are compact and provide an adequate amount of material for multiple restorations. The product is packaged with an illustrated instruction card. Room temperature storage enhances the convenience of **Futurabond DC**, allowing it to be stored in the operatory, rather than under refrigeration.

#### Ease of Application/ Surface Wettability and Viscosity

The *SingleDose* blister is easy to activate and mix with the applicator brush included, but there is no way



### Editors' Comments

- ◆ "SingleDose design is relatively easy to use."
- ◆ "Good wettability of the tooth surface."
- ◆ "Futurabond DC SingleDose provides fresh material for each case."
- ◆ "Versatile adhesive system."
- ◆ "Does not have a strong odor."

to determine visually if the product is adequately mixed. **Futurabond DC** consistently earned high ratings for its viscosity and wettability. Editors reported that it was easy to wet the tooth surface with the material and it was easy to apply. The entire bonding process is time-efficient.

#### Time Required for Bonding Procedure/Usefulness for Various Procedures

Editors reported that **Futurabond DC** was quick to use, with a 35-second total procedure time: 20 seconds for application, five seconds for air dispersal, and 10 seconds for light curing. The system is versatile in its compatibility with common restorative and cementation procedures.

#### Lack of Patient Sensitivity

No postoperative sensitivity was reported during the evaluation period.

### Clinical Tips

- ◆ To avoid bending the brush head, puncture the foil of the *SingleDose* with the handle end of the applicator brush if you do not use the *VOCO Single Tim* brush.
- ◆ When using **Futurabond DC** for post cementation, do not light cure the bonding agent in the post space. ■

## x-tra fil

### PACKABLE POSTERIOR BULK FILL COMPOSITE CURE 4MM IN 10 SEC

#### Advantages

- Use with Futurabond DC to bond, sculpt and cure a 4mm MOD restoration in less than 150 sec.
- 86% filled for excellent wear resistance
- Low 1.7% shrinkage for tight margins
- High radiopacity (330% AI) for easy x-ray identification
- No extra noisy and expensive equipment required
- Available in syringes and unit dose caps



#### Presentation

- REF 1740 Pack 1-5gm syringe, shade Universal  
REF 1741 Pack 20-0.25gm caps, shade Universal

## x-tra base®

### FLOWABLE POSTERIOR BULK BASE COMPOSITE CURE 4MM IN 10 SEC

#### Advantages

- 4mm cure in 10 sec. saves time\*
- Low shrinkage stress allows bulk fill speed
- High strength makes it suitable for open and closed sandwich technique
- Smart self-leveling properties for excellent wall adaptation without slumping out of maxillary restorations
- High radiopacity (350% AI) for easy x-ray identification
- Available in patented non-dripping NDT syringes or unit dose caps with extra long bendable needle tip
- Available in shades A2 and Universal

\*universal shade



- REF 1790 Pack 2-2gm syringe, shade Universal  
REF 1791 Pack 2-2gm syringe, shade A2  
REF 1794 Pack 16-0.25gm caps, shade Universal  
REF 1795 Pack 16-0.25gm caps, shade A2

VOCO America Inc.  
1245 Rosemont Drive  
Suite 140  
Indian Land · SC 29707  
www.vocoamerica.com  
infousa@voco.com  
Toll-free phone: 1-888-658-2584  
Fax: 1-888-849-3989

